

## Technical Properties for Oilon

	Norm	Unit i.e.	Value
<b><u>Physical Properties</u></b>			
Specific Gravity	ISO 1183	g/cm <sup>3</sup>	1.13
Water Absorption	DIN 53495	%	3
Chemical resistance	-	-	-
Maximum service temp	-	degrees C	100
Minimum service temp	-	degrees C	-40
<b><u>Mechanical Properties</u></b>			
Tensile strength at yeild	ISO 527	MPa	90/45
Elongation at yeild	ISO 527	%	4.5/20
Tensile strength at break	ISO 527	MPa	-
Elongation at break	ISO 527	%	>50
Impact strength	ISO 179	kJ/m <sup>2</sup>	0.B.
Notch impact strength	ISO 179	kJ/m <sup>2</sup>	9
Ball indentation (Rockwell)	ISO 2039	MPa	160/70
Shore D	DIN 53505	-	83
Flexural strength	ISO 178	MPa	-
Modulus elasticity	ISO 527	MPa	3000/1000
<b><u>Thermal Properties</u></b>			
Vicat softening temp	ISO 306	degrees C	-
Heat deflection Temp	ISO 75	degrees C	160
Coefficient of expansion	DIN 53752	K-1 x 10-4	0.85
Thermal conduct at 20	DIN 52612	W/(mxK)	0.28
<b><u>Electrical Properties</u></b>			
Volume resistivity	VDE 0303	x cm	>10 13
Surface resistivity	VDE 0303	-	>10 10
Dielectric constant @ 1MHz	DIN 53483	-	3.5/7
Diel. loss factor @ 1 MHz	DIN 53483	-	0.031/0.3
Dielectric strength	VDE 0303	kV/mm	20-50
Tracking resistance	DIN 53480	-	CTI 600
<b><u>Additional Data</u></b>			
Bondability	-	-	0
Friction Coeficient	DIN 53375	-	0.15
Flamability	UL 94	-	HB
<b><u>Chemical properties</u></b>			
Acid resistance			-
Hydroxid resistance (dilute)			+
Hydrocarbonat resistance			+/0
CKW resistance			-
Aromatic resistance			+/0
Ketone resistance			+
Resistance to hot water			+/0

[www.directplasticsonline.co.uk](http://www.directplasticsonline.co.uk)